3M Venture Tape[™] FSK Facing Tape 1525CW/1528CW

Product Description	3M TM Venture Tape TM FSK Facing Tape 1525CW is a foil/scrim/kraft (FSK) lamination coated with a cold weather solvent acrylic pressure sensitive adhest 3M TM Venture Tape TM FSK Facing Tape 1528CW is a 2.5" disc version of 1525CW.				
Product Construction	Backing Ad	thesive Colo	or	Standard Roll Lengt	
	FSK Ad	crylic Natu	ıral Aluminum	50 yds (45.7 m)	
Features	Excels in demanding temperature and humidity applicationsConforms well to irregular surfaces				
Typical Physical Properties	Note: The following technical information and data should be considered representativ or typical only and should not be used for specification purposes.				
	Test	Typical Value	Typical Value (Metr	ic) Test Method	
	Test Product Thickness	Typical Value 9.5 mils	Typical Value (Metr 0.24 mm	ic) Test Method PSTC-133	
	Product Thickness	9.5 mils	0.24 mm	PSTC-133 PSTC-101	
	Product Thickness Peel Adhesion Shear Adhesion Tensile Strength	9.5 mils 45 oz/in >24 hrs @ 2.2 psi 40 lb/in	0.24 mm 12.5 N/25 mm >24 hrs @ 15.2 kPa 180.8 N/25 mm	PSTC-133 PSTC-101 PSTC-107 PSTC-131	
	Product Thickness Peel Adhesion Shear Adhesion Tensile Strength Elongation	9.5 mils 45 oz/in >24 hrs @ 2.2 psi 40 lb/in 2%	0.24 mm 12.5 N/25 mm >24 hrs @ 15.2 kPa 180.8 N/25 mm 2%	PSTC-133 PSTC-101 PSTC-107	
	Product Thickness Peel Adhesion Shear Adhesion Tensile Strength	9.5 mils 45 oz/in >24 hrs @ 2.2 psi 40 lb/in 2%	0.24 mm 12.5 N/25 mm >24 hrs @ 15.2 kPa 180.8 N/25 mm	PSTC-133 PSTC-101 PSTC-107 PSTC-131	
Application Ideas	 Product Thickness Peel Adhesion Shear Adhesion Tensile Strength Elongation Service Temperature Applies easily to bo 	9.5 mils 45 oz/in >24 hrs @ 2.2 psi 40 lb/in 2% -40° to 240°F	0.24 mm 12.5 N/25 mm >24 hrs @ 15.2 kPa 180.8 N/25 mm 2% -40° to 116°C	PSTC-133 PSTC-101 PSTC-107 PSTC-131 PSTC-131	
Application Ideas	Product Thickness Peel Adhesion Shear Adhesion Tensile Strength Elongation Service Temperature	9.5 mils 45 oz/in >24 hrs @ 2.2 psi 40 lb/in 2% -40° to 240°F	0.24 mm 12.5 N/25 mm >24 hrs @ 15.2 kPa 180.8 N/25 mm 2% -40° to 116°C	PSTC-133 PSTC-101 PSTC-107 PSTC-131 PSTC-131	
Application Ideas Classifications	 Product Thickness Peel Adhesion Shear Adhesion Tensile Strength Elongation Service Temperature Applies easily to bo Use as a vapor seal 	9.5 mils 45 oz/in >24 hrs @ 2.2 psi 40 lb/in 2% -40° to 240°F	0.24 mm 12.5 N/25 mm >24 hrs @ 15.2 kPa 180.8 N/25 mm 2% -40° to 116°C	PSTC-133 PSTC-101 PSTC-107 PSTC-131 PSTC-131	

3M[™] Venture Tape[™] FSK Facing Tape 1525CW

Storage	Store in a clean, dry place. Temperature of 40-80°F (4-26°C) and 40 to 50% relative humidity are recommended.		
Shelf Life	To obtain best performance, use this product within 12 months from date of manufacture		
Technical Information	The technical information, recommendations and other statements contained in this docume based upon tests or experience that 3M believes are reliable, but the accuracy or completeness or information is not guaranteed.		
Product Use	Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the and performance of a 3M product in a particular application. Given the variety of factors that can af the use and performance of a 3M product, user is solely responsible for evaluating the 3M product determining whether it is fit for a particular purpose and suitable for user's method of application.		
Warranty, Limited Remedy, and Disclaimer	Unless an additional warranty is specifically stated on the applicable 3M product packaging or p literature, 3M warrants that each 3M product meets the applicable 3M product specification at th 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRES IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARF OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF T If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, a option, replacement of the 3M product or refund of the purchase price.		
Limitation of Liability	Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.		
	[ISO 9001]		
	This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.		

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

3M

Industrial Adhesives and Tapes Division

3M Center, Building 225-3S-06 St. Paul, MN 55144-1000 800-362-3550 • 877-369-2923 (Fax) www.3M.com/construction



Recycled Paper 40% pre-consumer 10% post-consumer 3M and Venture Tape are trademarks of 3M Company. Printed in U.S.A. ©3M 2015 All rights reserved. E 70-0709-4185-4