



Natural  
Rubber Latex



Lab & Utility

# Conform<sup>®</sup>+

69-210 69-318  
Natural Rubber Latex Glove

## Handle the most intricate and delicate products with incredible sensitivity

### FEATURES AND BENEFITS:

#### Comfort, Strength and Sensitivity

The strength and comfort of 100% natural rubber latex, 5 mil thickness for the highest degree of sensitivity

#### 2 versions available to better fit your needs

69-210: Powdered, smooth Grip

69-318: Powder Free, textured finish  
for better grip

#### Food compliant

Conform<sup>®</sup> gloves comply with FDA food handling requirements (21 CFR 177.2600).



**Ansell**

### TECHNICAL DATA SHEET:

#### PRODUCT INFORMATION:

	69-210	69-318
<b>Material</b>	Natural Rubber Latex	
<b>Color</b>	Natural	
<b>Glove Design</b>	Ambidextrous, Powdered, Smooth Grip	Ambidextrous, Powder Free, textured Grip
<b>Cuff</b>	Beaded Cuff	
<b>Audit Standards</b>	ISO 9001:2008, ISO 13485:2003, US FDA 21 CFR PART 820 (QSR), and Canadian MDR	
<b>Quality Control</b>	Incoming for both raw materials and packaging materials, in-process (QA pre-packing inspection) and final release (QA pre-shipment inspection) for all gloves produced.	
<b>Packaging</b>	100 gloves per dispensers, 10 dispensers per shipper carton, 1000 gloves per shipper cartons	
<b>Storage</b>	Keep out of direct sunlight; store in a cool and dry place. Keep away from sources of ozone or ignition.	
<b>Country of Origin</b>	Malaysia	

#### PHYSICAL PROPERTIES:

PROPERTY	SIZE	TYPICAL VALUES					TESTING METHOD
		XS	S	M	L	XL	
Length (mm)	69-210	NA	240	240	240	240	ASTM D3767/EN 420
	69-318	240	240	240	240	240	
Average Palm Width (mm)	69-210	NA	80	95	102	111	ASTM D3767/EN 420
	69-318	75	85	95	106	116	
Freedom from Holes (Inspection level I)	1.5 AQL					ASTM D5151/EN 374-2	
Palm Thickness Single Wall	69-210	69-318				ASTM D3767/EN 420	
	(mm: 0.10) / (mils: 4)	(mm: 0.12) / (mils: 5)					
	<b>BEFORE AGING</b>			<b>AFTER AGING</b>			
Ultimate Tensile Strength	Min 18 Mpa			Min 14 Mpa		ASTM D 412-06a	
Allongement à la rupture (%)	Min 650			Min 500		ASTM D 412-06a	

#### ORDERING INFORMATION:

	SIZE	XS	S	M	L	XL
69-210	ASPEN	NA	516704	516705	516706	516707
	ORACLE	NA	104986	104987	104988	104989
69-318	ASPEN	516699	516700	516701	516702	516703
	ORACLE	NA	105072	105073	105074	105075



For additional information visit us at [www.ansell.com](http://www.ansell.com), or call us at  
 North America, Latin America and Caribbean: +1800 800 0444  
 Asia Pacific: +852 2185 0600  
 Europe: +32 2 528 74 00  
 Australia: +61 3 9270 7270

® and ™ are trademarks owned by Ansell Limited or one of its affiliates. © 2013 All Rights Reserved.